








FOND DU LAC ROCKWOOD

SPECIFICATIONS

THIN VENEER FULL VENEER **bimobject**

	ORIGIN	FOND DU LAC, WISCONSIN
	INFO	50% SPLITFACE, 50% BEDFACE (STONEGATE & DIMENSIONAL)
	PATTERN	SAWN DIMENSIONAL AND RANDOM NATURAL COURSE, ASHLAR
	COLOR	SILVER, LIGHT TO DARK GRAY, BROWN
	AREA	37-40 SQFT / TON (FULL) 12-15 LBS/SQFT (THIN)
	HEIGHT	SAWN 7-3/4", 10-1/2" & NATURAL HEIGHTS 2"- 6"
	LENGTH	6" - 36" THIN VENEER CORNERS: 6"-13"
	WIDTH	FULL: 3"-5" (4") THIN: 3/4"-1/2"
	DENSITY	175 LB/FT ³ (FDL)



ASTM - C170

FOND DU LAC COMPRESSIVE STRENGTH

23,530 PSI	PERPENDICULAR TO RIFT, WET
31,010 PSI	PERPENDICULAR TO RIFT, DRY
26,050 PSI	PARALLEL TO RIFT, WET
28,300 PSI	PARALLEL TO RIFT, DRY

ASTM - C97

ABSORPTION & SPECIFIC GRAVITY

.32%	WATER ABSORPTION
2.80	BULK SPECIFIC GRAVITY

ASTM - C880

FLEXURAL STRENGTH

1,640 PSI	AVERAGE FLEXURAL STRENGTH, WET
2,040 PSI	AVERAGE FLEXURAL STRENGTH, DRY

