










COTTAGE MANOR

SPECIFICATIONS

THIN VENEER FULL VENEER bimobject

	ORIGIN	OAKFIELD + FOND DU LAC, WISCONSIN
	INFO	40% SPLITFACE, 40% BEDFACE, 20% SEAMFACE (STONEGATE, DIMENSIONAL, RUSTIC)
	PATTERN	NATURAL & SAWN COURSE, ASHLAR
	COLOR	GOLD, GRAY, SILVER, BEIGE, EARTHY TONE SPLITFACE, GRAY / BROWN / TAN BEDS
	AREA	37-38 SQFT / TON (FULL) 12-15 LBS/SQFT (THIN)
	HEIGHT	RANDOM 2" - 6", SNAPPED BEDS 8", 10", 12" (+/- 1")
	LENGTH	6" - 30" THIN VENEER CORNERS: 6"-13"
	WIDTH	FULL: 3"-5" (4") THIN: 3/4"-1/2"
	DENSITY	176 LB/FT ³ (OAK) 175 LB/FT ³ (FDL)



ASTM - C170

FOND DU LAC
COMPRESSIVE STRENGTH 

23,530 PSI	PERPENDICULAR TO RIFT, WET
31,010 PSI	PERPENDICULAR TO RIFT, DRY
26,050 PSI	PARALLEL TO RIFT, WET
28,300 PSI	PARALLEL TO RIFT, DRY

ASTM - C97 ABSORPTION & SPECIFIC GRAVITY

OAK: .29%	FDL: .32	WATER ABSORPTION
OAK: 2.81	FDL: 2.80	BULK SPECIFIC GRAVITY

ASTM - C170

OAKFIELD
COMPRESSIVE STRENGTH 

24,740 PSI	PERPENDICULAR TO RIFT, WET
31,490 PSI	PERPENDICULAR TO RIFT, DRY
27,060 PSI	PARALLEL TO RIFT, WET
25,060 PSI	PARALLEL TO RIFT, DRY

ASTM - C880 FLEXURAL STRENGTH

1,010 PSI - 1,640 PSI	AVERAGE FLEXURAL STRENGTH, WET
1,020 PSI - 2,040 PSI	AVERAGE FLEXURAL STRENGTH, DRY

