










# FOND DU LAC STONEGATE - TUMBLED

## SPECIFICATIONS

THIN VENEER  FULL VENEER  **bimobject**

	ORIGIN	FOND DU LAC, WISCONSIN
	INFO	100% SPLITFACE, MACHINE CUT - TUMBLED
	PATTERN	NATURAL, RANDOM ASHLAR
	COLOR	SILVER, LIGHT TO DARK GRAY, WHITE
	AREA	40 SQFT / TON (FULL VENEER)
	HEIGHT	RANDOM 2" - 6", 6" - 10" (JUMPERS)
	LENGTH	6" - 30"
	WIDTH	FULL 3" - 5" (4"), THIN 3/4" - 1/2" (1")
	DENSITY	175 LB/FT <sup>3</sup>



## ASTM - C170

FOND DU LAC  
COMPRESSIVE STRENGTH 

23,530 PSI	PERPENDICULAR TO RIFT, WET
31,010 PSI	PERPENDICULAR TO RIFT, DRY
26,050 PSI	PARALLEL TO RIFT, WET
28,300 PSI	PARALLEL TO RIFT, DRY

## ASTM - C97

ABSORPTION & SPECIFIC GRAVITY 

.32%	WATER ABSORPTION
2.80	BULK SPECIFIC GRAVITY

## ASTM - C880

FLEXURAL STRENGTH 

1,640 PSI	AVERAGE FLEXURAL STRENGTH, WET
2,040 PSI	AVERAGE FLEXURAL STRENGTH, DRY

