










# ANTIQUE CAMBRIAN

## SPECIFICATIONS

THIN VENEER  FULL VENEER  bimobject

	ORIGIN	MOSINEE, WISCONSIN - SANDSTONE
	INFO	100% SPLITFACE, MACHINE CUT
	PATTERN	NATURAL COURSE, RANDOM ASHLAR
	COLOR	CREAM, LIGHT TAN, BROWN, SOME HORIZONTAL STRIPING
	AREA	37-40 SQFT / TON (FULL) 12-15 LBS/SQFT (THIN)
	HEIGHT	RANDOM 2" - 6", JUMPERS 6" - 9"
	LENGTH	6" - 30" THIN VENEER CORNERS: 6" - 13"
	WIDTH	FULL: 3" - 5" (4") THIN: 3/4" - 1/2"
	DENSITY	152 LB/FT <sup>3</sup>



### ASTM - C170

### COMPRESSIVE STRENGTH

18,360 PSI	PERPENDICULAR TO RIFT, WET
17,510 PSI	PERPENDICULAR TO RIFT, DRY
15,300 PSI	PARALLEL TO RIFT, WET
16,530 PSI	PARALLEL TO RIFT, DRY

### ASTM - C97

### ABSORPTION & SPECIFIC GRAVITY

1.04%	WATER ABSORPTION
2.44	BULK SPECIFIC GRAVITY

### ASTM - C880

### FLEXURAL STRENGTH

460 PSI	AVERAGE FLEXURAL STRENGTH, WET
480 PSI	AVERAGE FLEXURAL STRENGTH, DRY

