










SPECIFICATIONS

THIN VENEER FULL VENEER bimobject

| | | |
|---|---------|---|
|  | ORIGIN | BEAVER DAM, WISCONSIN |
|  | INFO | 100% SPLITFACE, MACHINE CUT VENEER |
|  | PATTERN | NATURAL, RANDOM ASHLAR |
|  | COLOR | TAN, BUFF, BROWN |
|  | AREA | 37 - 40 SQFT / TON (FULL) 12-15 LBS/SQFT (THIN) |
|  | HEIGHT | RANDOM 2" - 6", JUMPERS 6"-9" |
|  | LENGTH | 6" - 24" THIN VENEER CORNERS: 6"-13" |
|  | WIDTH | FULL: 3"-5" (4") THIN: 3/4"- 1/2" |
|  | DENSITY | 173 LB/FT ³ |



ASTM - C170

COMPRESSIVE STRENGTH

| | |
|------------|----------------------------|
| 24,970 PSI | PERPENDICULAR TO RIFT, WET |
| 26,360 PSI | PERPENDICULAR TO RIFT, DRY |
| 25,110 PSI | PARALLEL TO RIFT, WET |
| 29,220 PSI | PARALLEL TO RIFT, DRY |

ASTM - C97

ABSORPTION & SPECIFIC GRAVITY

| | |
|-------|-----------------------|
| 0.57% | WATER ABSORPTION |
| 2.76 | BULK SPECIFIC GRAVITY |

ASTM - C880

FLEXURAL STRENGTH

| | |
|-------------------|--------------------------------|
| 1,100 - 1,260 PSI | AVERAGE FLEXURAL STRENGTH, WET |
| 1,430 - 1,590 PSI | AVERAGE FLEXURAL STRENGTH, DRY |

